

### In the Claims

1. (Cancelled)
2. (Currently Amended) A martensitic stainless steel seamless pipe containing:

less than about 0.0100% of C;

less than about 0.0100% of N;

about 10% to about 14% of Cr;

about 4% to about 7% of Ni;

about 0.05% to about 1.0% of Si;

about 0.1% to about 2.0% of Mn;

about 0.3% or less of P;

about 0.010% or less of S;

about 0.001% to about 0.10% of Al;

0.02% to 0.1% of V;

one or more selected from the group consisting of about 4% or less of Cu, about 4% or less of Co, about 4% or less of Mo, and about 4% or less of W; and

one or more selected from the group consisting of about 0.15% or less of Ti, about 0.10% or less of Nb, ~~about 0.10% or less of V~~, about 0.10% or less of Zr, about 0.20% or less of Hf, and about 0.20% or less of Ta on a mass basis, the remainder being Fe and unavoidable impurities, wherein the content  $C_{sol}$  defined by the following equation (1) is equal to or less than 0.0050%:

$$C_{sol} = C - 1/3 \times C_{pre} \quad (1)$$

where  $C_{pre} = 12.0 \{Ti/47.9 + 1/2 (Nb/92.9 + Zr/91.2) + 1/3 (V/50.9 + Hf/178.5 + Ta/180.9) - N/14.0\}$  or  $C_{pre} = 0$  when  $C_{pre} < 0$ , where C represents the carbon content, Ti

represents the titanium content, Nb represents the niobium content, Zr represents the zirconium content, V represents the vanadium content, Hf represents the hafnium content, Ta represents the tantalum content, and N represents the nitrogen content on a mass basis, and martensite in ~~the~~ a weld heat affected zone of the steel pipe is substantially free of Cr depleted zones.

3. (Previously Presented) The martensitic stainless steel seamless pipe according to Claim 2 further containing one or more selected from the group consisting of about 0.010% or less of Ca, about 0.010% or less of Mg, about 0.010% or less of REM, and about 0.010% or less of B on a mass basis.

4. (Currently Amended) A martensitic stainless steel seamless pipe containing:

- less than about 0.0100% of C;
- less than about 0.0100% of N;
- about 10% to about 14% of Cr;
- about 4% to about 7% of Ni;
- about 0.05% to about 1.0% of Si;
- about 0.1% to about 2.0% of Mn;
- about 0.03% or less of P;
- about 0.010% or less of S;
- about 0.001% to about 0.10% of Al;
- about 0.02% to about 0.10% of V;
- about 0.0005% to about 0.010% of Ca; and

one or more selected from the group consisting of about 4% or less of Cu, about 4% or less of Co, about 4% or less of Mo, and about 4% or less of W on a mass basis, the remainder being Fe and unavoidable impurities,

wherein the content  $C_{sol}$  defined by the following equation (1) is equal to or less than 0.0050%:

$$C_{sol} = C - 1/3 \times C_{pre} \quad (1)$$

where  $C_{pre} = 12.0 \{Ti/47.9 + 1/2 (Nb/92.9 + Zr/91.2) + 1/3 (V/50.9 + Hf/178.5 + Ta/180.9) - N/14.0\}$  or  $C_{pre} = 0$  when  $C_{pre} < 0$ , where  $C$  represents the carbon content,  $Ti$  represents the titanium content,  $Nb$  represents the niobium content,  $Zr$  represents the zirconium content,  $V$  represents the vanadium content,  $Hf$  represents the hafnium content,  $Ta$  represents the tantalum content, and  $N$  represents the nitrogen content on a mass basis, and martensite in the a weld heat affected zone of the steel pipe is substantially free of Cr depleted zones.

5. (Previously Presented) The martensitic stainless steel seamless pipe according to Claim 4 further containing one or more selected from the group consisting of about 0.15% or less of  $Ti$ , about 0.10% or less of  $Nb$ , about 0.10% or less of  $Zr$ , about 0.20% or less of  $Hf$ , and about 0.20% or less of  $Ta$  on a mass basis.

6. (Cancelled)

7. (Previously Presented) A seamless line pipe comprising the martensitic stainless steel pipe according to Claim 2.

8. (Previously Presented) A line pipe comprising the martensitic stainless steel seamless pipe according to Claim 3.

9. (Previously Presented) A line pipe comprising the martensitic stainless steel seamless pipe according to Claim 4.

10. (Previously Presented) A line pipe comprising the martensitic stainless steel seamless pipe according to Claim 5.

11. (Cancelled)

12. (Previously Presented) A welded structure comprising the martensitic stainless steel seamless pipe according to Claim 2, welded to a member.

13. (Previously Presented) A welded structure comprising the martensitic stainless steel seamless pipe according to Claim 3, welded to a member.

14. (Previously Presented) A welded structure comprising the martensitic stainless steel seamless pipe according to Claim 4, welded to a member.

15. (Previously Presented) A welded structure comprising the martensitic stainless steel seamless pipe according to Claim 5, welded to a member.

16. (Cancelled)

17. (Previously Presented) A welded structure comprising the seamless line pipe according to Claim 7.

18. (Previously Presented) A welded structure comprising the seamless line pipe according to Claim 8.

19. (Previously Presented) A welded structure comprising the seamless line pipe according to Claim 9.

20. (Previously Presented) A welded structure comprising the seamless line pipe according to Claim 10.